


6165 W Detroit St. • Chandler AZ 85226  
 +1 (602) 276-0406 • +1 (800) 528-8242 • FAX +1 (480) 961-0513  
 www.crafco.com

**READ BEFORE USING THIS PRODUCT**

**GENERAL** CrafcO Asphalt Rubber 541 sealant is a hot-applied asphalt based product used to seal and fill cracks and joints in asphalt or Portland cement concrete pavements in moderate to hot climates. Asphalt Rubber 541 is supplied in solid form which when melted and properly applied forms an adhesive and flexible compound that resists cracking in the winter and resists flow at summer temperatures. Asphalt Rubber 541 is used in highway, street, airfield and parking lot pavements and is applied to pavement cracks and joints using pressure feed melter applicators. At application temperature, Asphalt Rubber 541 is a higher viscosity, non self-leveling product. Asphalt Rubber 541 contains virgin rubber, vulcanized granulated crumb rubber, and selected paving asphalt. Asphalt rubber 541 is produced to meet requirements of the Texas Highway Department for Rubber Asphalt Crack Sealer. VOC = 0 g/l.

**USAGE GUIDELINES** Asphalt Rubber 541 is applicable for Sealant/Reservoir or Filler / Overband Use in moderate to hot climates with low and high pavement temperatures identified in the charts. Pavement temperatures for the project location are determined at 98% reliability using FHWA LTPPBIND V 3.1, and sealant or filler use is determined following CrafcO Product Selection procedures.



High Temperature (°C)

°C	52	58	64	70	76	82
Low Temperature (°C)	-10					
	-16					
	-22					
	-28					
	-34					
	-40					
	-46					

**Sealant / Reservoir Use**

High Temperature (°C)

°C	52	58	64	70	76	82
Low Temperature (°C)	-10					
	-16					
	-22					
	-28					
	-34					
	-40					
	-46					

**Filler / Overband Use**

**SPECIFICATION CONFORMANCE** CrafcO Asphalt Rubber 541 meets all requirements of State of Texas Department of Highways for Rubber Asphalt Crack Sealer (Texas SDHPT Item 300.2 Class B) and exceeds requirements of ASTM D5078.

Test	Texas SDHPT 300.2 Class B Limits
Minimum Application Temperature	380°F (193°C)
Maximum Heating Temperature	400°F (204°C)
Cone Penetration, 77°F (25°C)	30-50
Cone Penetration, 32°F (0°C), 200 g 60 sec.	12 min.
Softening Point (ASTM D36)	170°F (77°C) min.
Flash Point, modified C.O.C.	400°F (204°C) min.
Virgin Rubber Polymer, % by wt.	2% min.
Granulated vulcanized rubber, % by wt.	13-17%
Bond, 20°F (-7°C), 50% ext	Pass 3 cycles.

**INSTALLATION** Prior to use, the user must read and follow Installation Instructions for Hot-Applied RoadSaver, PolyFlex, Parking Lot and Asphalt Rubber Products to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. These instructions are provided with each pallet of product.

**PACKAGING** Product is supplied in either cardboard boxes, or in meltable, boxless PLEXI-melt packaging. Both package types are labeled in accordance with OSHA, GHS, and specification requirements; are sold by net weight; are interlock stacked on 48 x 40 in. (122 x 102 cm) 4-way pallets; can be stored outside; and are covered with a weather resistant pallet cover and 2 layers of UV protected stretch wrap.

- o **BOX** packaging consists of cardboard boxes containing approximately 30 lb. (13.6 kg) of product with 75 boxes per pallet, weighing approximately 2250 lb. (1020 kg). Boxes contain a quick melting release film for easy removal and are taped closed, without any staples.
- o **PLEXI-melt** packaging consists of 30 lb. (13.6 kg) blocks of product with 70 packages per pallet, weighing 2100 lb. (952 kg). To use, the pallet wrap is removed, and individual blocks are placed in the melter. There are no cardboard boxes or other cardboard components to open, empty, handle, or dispose of. PLEXI-melt packaging quickly melts into the product without affecting specification conformance.

**WARRANTY** CRAFCO, Inc. warrants that CRAFCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, CrafcO shall not be responsible for improperly applied or misused products. Remedies against CrafcO, Inc., as agreed to by CrafcO, are limited to replacing nonconforming product or refund (full or partial) of purchase price from CrafcO, Inc. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by CrafcO, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow CrafcO recommendations for product installation.**