




READ BEFORE USING THIS PRODUCT

GENERAL Crafcro RoadSaver CA Type 5 is a hot-applied, asphalt based product used to seal and fill cracks and joints in asphalt and Portland cement concrete pavements in cool climates. RoadSaver CA Type 5 is specifically formulated to meet CalTrans Standard Specifications 37-5.02 Type 5 for Crack Treatment. RoadSaver CA Type 5 is supplied in solid form which when melted and properly applied forms a highly adhesive and flexible compound that resists cracking in the winter and resists flow and pick-up at summer temperatures. RoadSaver CA Type 5 is used in highway, street, and parking lot pavements and is applied to pavement cracks using either pressure feed melter applicators or pour pots. At application temperature, RoadSaver CA Type 5 is a free flowing self leveling product which flows and penetrates cracks. RoadSaver CA Type 5 is formulated as an economical yet effective pavement maintenance crack filler and sealant product. VOC = 0 g/l.

USAGE GUIDELINES RoadSaver CA Type 5 is applicable for Sealant/Reservoir Use and Filler/Overband Use in cool climates with low and high pavement temperatures identified in the charts. Pavement temperatures for the project location are determined at 98% reliability using FHWA LTPPBind V 3.1, and sealant or filler use is determined following Crafcro Product Selection Procedures.



SPECIFICATION CONFORMANCE Crafcro RoadSaver CA Type 5 conforms to CalTrans Standard Specifications 37-5.02 Type 5 when heated in accordance with ASTM D5167 to the maximum heating temperature are as follows:

<u>Test</u>	<u>CalTrans 37-5.02 Type 5</u>
Softening Point (ASTM D36/D36M)	84°C min
Cone Penetration at 77°F (ASTM D5329)	90 max
Resiliance at 77°F unaged (ASTM D5329)	40 – 80%
Flexibility (ASTM D3111 modified*)	Pass at -28°C
Tensile Adhesion (ASTM D5329)	500% min
Specific Gravity (ASTM D70)	1.25 max
Asphalt Compatibility (ASTM D5329)	Pass
Sieve Test (Certification non-soluble components pass #16 sieve)	Pass 100%
Maximum Heating Temperature	400°F (204°C)
Minimum Application Temperature	380°F (193°C)
*6.4 mm thick, 6.4 mm mandrel, 180 degree bend in 2 seconds	

INSTALLATION The unit weight of Crafcro RoadSaver CA Type 5 is 10.2 lbs. per gallon (1.22 kg/L) at 60°F (15.5°C). Prior to use, the user must read and follow Installation Instructions for Hot-Applied RoadSaver, PolyFlex, Parking Lot and Asphalt Rubber Products to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. These instructions are provided with each pallet of product.

PACKAGING Product is supplied in either cardboard boxes, or in meltable, boxless PLEXI-melt packaging. Both package types are labeled in accordance with OSHA, GHS, and specification requirements; are sold by net weight; are interlock stacked on 48 x 40 in. (122 x 102 cm) 4-way pallets; can be stored outside; and are covered with a weather resistant pallet cover and 2 layers of UV protected stretch wrap.

- o **BOX** packaging consists of cardboard boxes containing approximately 30 lb. (13.6 kg) of product with 75 boxes per pallet, weighing approximately 2250 lb. (1020 kg). Boxes contain a quick melting release film for easy removal and are taped closed, without any staples.
- o **PLEXI-melt** packaging consists of 30 lb. (13.6 kg) blocks of product with 70 packages per pallet, weighing 2100 lb. (952 kg). To use, the pallet wrap is removed, and individual blocks are placed in the melter. There are no cardboard boxes or other cardboard components to open, empty, handle, or dispose of. PLEXI-melt packaging quickly melts into the product without affecting specification conformance.

WARRANTY CRAFCO, Inc. warrants that CRAFCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, Crafcro shall not be responsible for improperly applied or misused products. Remedies against Crafcro, Inc., as agreed to by Crafcro, are limited to replacing nonconforming product or refund (full or partial) of purchase price from Crafcro, Inc. All claims for breach of this warranty must be

made within three (3) months of the date of use or twelve (12) months from the date of delivery by Crafc0, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow Crafc0 recommendations for product installation.**