


READ BEFORE USING THIS PRODUCT

GENERAL Crafcro RoadSaver 960 Gray Sealant is a gray colored, hot applied, single component, elastically modified composition of non-asphaltic ingredients and modifiers used to fill cracks and joints in asphalt and portland cement concrete pavements. RoadSaver 960 Gray Sealant is supplied in powder/granular form in meltable bags which when melted and properly applied forms an adhesive and flexible compound that resists cracking in the winter and is resistant to flow at summer temperatures. RoadSaver 960 Gray Sealant is used in highway, street and airfield pavements where the gray color is desired. VOC=0 g/l.

USAGE GUIDELINES RoadSaver 960 Gray Sealant is applicable for Sealant/ Reservoir use and Filler/Overband Use in moderate climates with low and high pavement temperatures identified in the charts. Pavement temperatures for the project location are determined at 98% reliability using FHWA LTPPBind V 3.1, and sealant or filler use is determined following Crafcro Product Selection Procedures.



		High Temperature (°C)					
		52	58	64	70	76	82
Low Temperature (°C)	-10	Shaded	Shaded	Shaded			
	-16	Shaded	Shaded	Shaded			
	-22						
	-28						
	-34						
	-40						
	-46						

Sealant / Reservoir Use

		High Temperature (°C)					
		52	58	64	70	76	82
Low Temperature (°C)	-10	Shaded	Shaded	Shaded			
	-16	Shaded	Shaded	Shaded			
	-22						
	-28						
	-34						
	-40						
	-46						

Filler / Overband Use

SPECIFICATION CONFORMANCE Crafcro RoadSaver 960 Gray Sealant meets all requirements of ASTM D6690 (AASHTO M324), Type I, “Joint and Crack Sealants, Hot-applied, for Concrete and Asphalt Pavements”.

<u>Test</u>	<u>ASTM D6690, AASHTO M324 Type I Spec. Limits</u>
Cone Penetration at 25°F (ASTM D5329)	90 max
Softening Point (ASTM D36)	80°C minimum
Bond, non-immersed, -18°C, 50% ext.	Pass 5 cycles
Asphalt Compatibility (ASTM D5329)	Pass
Maximum Heating Temperature	400°F (204°C)
Minimum Application Temperature	380°F (193°C)

INSTALLATION The unit weight of Crafcro RoadSaver 960 Gray Sealant is 11.3 lbs. per gallon (1.35 kg/L) at 60°F (15.5°C). Prior to use, the user must read and follow Installation Instructions for Hot-Applied RoadSaver, PolyFlex, Parking Lot and Asphalt Rubber Products to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. These instructions are provided with each pallet of product.

PACKAGING Product is supplied in meltable bags each containing 35 +/- 2 pounds (15.8 +/- 1 kg) of product. Bags are stacked and stretch wrapped on pallets containing approximately 2700 pounds (1225 kg). To use, the pallet wrap is removed and individual bags are placed in melter. There are no cardboard boxes or other components to open, empty, handle or dispose of. The bag melts into the product without affecting specification conformance.

WARRANTY CRAFCO, Inc. warrants that CRAFCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, Crafcro shall not be responsible for improperly applied or misused products. Remedies against Crafcro, Inc., as agreed to by Crafcro, are limited to replacing nonconforming product or refund (full or partial) of purchase price from Crafcro, Inc. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by Crafcro, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow Crafcro recommendations for product installation**