


READ BEFORE USING THIS PRODUCT

GENERAL Crafcro RoadSaver 963 Gray Sealant is a gray colored, hot applied, single component, elastically modified composition of non-asphaltic ingredients and modifiers used to fill cracks and joints in asphalt and portland cement concrete pavements. RoadSaver 963 Gray Sealant is supplied in powder/granular form in meltable bags which when melted and properly applied forms an adhesive and flexible compound that resists cracking in the winter and is resistant to flow at summer temperatures. RoadSaver 963 Gray Sealant is used in highway, street and airfield pavements where the gray color is desired. VOC=0 g/l.

USAGE GUIDELINES RoadSaver 963 Gray Sealant is applicable for Sealant/ Reservoir use and Filler/ Overband use with low and high pavement temperatures identified in the charts. Pavement temperatures for the project location are determined at 98% reliability using FHWA LTPPBind V 3.1, and sealant or filler use is determined following Crafcro Product Selection Procedures.



		High Temperature (°C)					
		52	58	64	70	76	82
Low Temperature (°C)	-10	■	■	■	■		
	-16						
	-22						
	-28						
	-34						
	-40						
	-46						

Sealant / Reservoir Use

		High Temperature (°C)					
		52	58	64	70	76	82
Low Temperature (°C)	-10	■	■	■	■		
	-16	■	■	■	■		
	-22						
	-28						
	-34						
	-40						
	-46						

Filler / Overband Use

SPECIFICATION CONFORMANCE Crafcro RoadSaver 963 Gray Sealant meets the following requirements when heated in accordance with ASTM D5167

<u>Test</u>	<u>Crafcro Roadsaver 963 Specification Limits</u>
Cone Penetration at 77°F (ASTM D5329)	75 maximum
Cone Penetration at 122°F (ASTM D5329)	120 maximum
Flow at 140°F (ASTM D5329)	5.0 mm maximum
Resilience, 77°F, % (D5329)	60 minimum
Flexibility, 90° bend, ¼" mandrel, 2 seconds	Pass @ 20°F
Maximum Heating Temperature	400°F (204°C)
Minimum Application Temperature	380°F (193°C)

INSTALLATION The unit weight of Crafcro RoadSaver 963 Gray Sealant is 12.0 lbs. per gallon (1.44 kg/L) at 60°F (15.5°C). Prior to use, the user must read and follow Installation Instructions for Hot-Applied RoadSaver, PolyFlex, Parking Lot and Asphalt Rubber Products to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. These instructions are provided with each pallet of product.

PACKAGING Product is supplied in meltable bags each containing 35 pounds (15.8 kg) of product with 60 bags per pallet. Bags are stacked and stretch wrapped on pallets containing approximately 2100 pounds (953 kg). To use, the pallet wrap is removed and individual bags are placed in melter. There are no cardboard boxes or other components to open, empty, handle or dispose of. The bag melts into the product without affecting specification conformance.

WARRANTY CRAFCO, Inc. warrants that CRAFCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, Crafcro shall not be responsible for improperly applied or misused products. Remedies against Crafcro, Inc., as agreed to by Crafcro, are limited to replacing nonconforming product or refund (full or partial) of purchase price from Crafcro, Inc. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by Crafcro, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow Crafcro recommendations for product installation**