

READ BEFORE USING THIS PRODUCT

GENERAL DESCRIPTION: ACTION PAVE[®] RT CLASSIC is a heavy-duty, concentrated, refined coal tar emulsion sealer specifically designed to protect and beautify asphalt pavements. ACTION PAVE[®] RT CLASSIC is based on carefully selected grades of refined tar, minerals and specialty additives. ACTION PAVE[®] RT CLASSIC has an extraordinary degree of toughness and water repellency, unmatched by any competitive sealer. ACTION PAVE[®] RT CLASSIC forms a tough, durable and flexible coating that protects asphalt pavements from the damaging elements of weather, water penetration, de-icing salts, traffic damage, surface raveling/checking, gasoline and other petrochemicals. ACTION PAVE[®] RT CLASSIC is recommended for use on many asphalt pavement surfaces, including home driveways, commercial parking lots, apartment complexes, restaurants, schools, gas stations, truck terminals, airfield taxiways, parking areas, shoulders, and many more. ACTION PAVE[®] RT CLASSIC is mixed on the jobsite with water and sand to provide proper application consistency, skid resistance, and wear resistance. Polymer additives may also be added at the jobsite for improved durability. ACTION PAVE[®] RT CLASSIC is available in a variety of forms including concentrate, ready mix, sand mix & sand ready mix. The combination of state-of-the-art technology in manufacturing and raw material selection translates into the following outstanding properties. VOC <50 g/l.

Outstanding Properties

- Outstanding Toughness and Durability – ACTION PAVE[®] RT CLASSIC is widely known as the workhorse of the industry when it comes to the protection and preservation of asphalt surfaces.
- Superior Flexibility – Ability to bridge minor surface (non-working) cracks in the pavement to eliminate water penetration and extend the life of asphalt surfaces.
- Beautifies While It Protects – Dries to an appealing dark charcoal color that enhances the value of the property. Snow removal becomes easier and traffic markings last longer.

SPECIFICATION CONFORMANCE ACTION PAVE[®] RT CLASSIC meets all requirements of ASTM Specification D5727, “Standard Specification for Emulsified Refined Coal Tar (Mineral Colloid Type)”, Federal Specification R-P-355e, “Pitch, Coal Tar Emulsion (Coating for Bituminous Pavements)”, and exceeds requirements of ASTM D 3320, “Standard Specification for Emulsified Coal-Tar Pitch (Mineral Colloid Type)” when tested according to ASTM D2939. ACTION PAVE[®] RT CLASSIC can be used as the base material for meeting requirements of ASTM D4866, D6945 and D6946.

Test

Uniformity

Wet Film Continuity
 Resistance to Freezing
 Density, 25C (77F)
 Residue by Evaporation
 Water Content
 Resistance to Volatilization
 Solubility of Residue in CS₂
 Ash Content of Residue
 Drying time, firm set
 Resistance to Heat
 Resistance to Kerosene
 Resistance to Water
 Flexibility
 Impact Resistance

ASTM D5727 and

Fed R-P-355e Spec. Limits

No Separation, coagulation, or settlement that cannot be overcome by moderate stirring
 Uniform homogeneous consistency
 Return to homogeneous when stirred
 1.2 g/ml (10 lb/gal) minimum
 47% minimum
 53% maximum
 10% maximum
 20% minimum
 30-40%
 8 h maximum
 No blistering, sagging, slipping
 No adhesion loss, penetration, or film softening
 No adhesion loss, blistering, or re-emulsification
 No flaking, cracking, or adhesion loss
 No chipping, flaking, cracking, or adhesion loss more than 6.4mm (1/4inch) beyond the periphery of the impact

Mix Design Recommendations

ACTION PAVE[®] RT CLASSIC is supplied in concentrated form that is field mixed with water and sand prior to installation. Polymer additives may also be used to improve durability. Recommended application consists of using 2 coats in low and moderate traffic areas, and using 3 coats in heavy traffic areas. Recommended mixture ranges and application rates are as follows:

USE AREA	COAT	ACTION PAVE [®] RT CLASSIC (Gallons)	WATER ⁽¹⁾ (Gallons)	SAND ⁽²⁾ (Pounds)	POLYMER ⁽³⁾ (Gallons)	APPLICATION RATE (Gallons/ Square yard)
LOW TRAFFIC - home driveways, Parking lots, walkways, bike paths	1 st	100	30-40	200-300	0-3	0.15-0.20
	2 nd	100	25-40	0-300	0-3	0.10-0.15
MODERATE TRAFFIC - airfields, Highway shoulders, gas stations	1 st	100	30-50	300-500	0-4	0.15-0.20
	2 nd	100	30-50	0-500	0-4	0.10-0.15

HEAVY TRAFFIC - Airfield taxiways, malls, Commercial parking lots, service plazas	1 st	100	30-60	400-600	0-5	0.15-0.20
	2 nd	100	30-60	400-600	0-5	0.15-0.20
	3 rd	100	30-40	0-500	0-4	0.10-0.15

NOTES:

1. Water shall be clean and potable
2. Sand shall be clean, angular quartz or slag sand meeting AFS 50-70 gradation, or equivalent
3. Polymer shall be Macro-Flex, Max-Dri, Advantage 4 or equivalent

Important Weather Limitations for Application

- Surface and air temperature should be a minimum of 50° F (10° C) and rising.
- Do not apply on rainy, foggy, or extremely humid days, or when rain is in the forecast within 24 hours.
- If the pavement temperature is over 100° (38°C), dampen the pavement with a fine mist of water to facilitate even spreading. Do not allow water to puddle on the surface

Application Tools

Use conventional tools including brush, rubber squeegee or spray rig. Clean up using water. Do not discard washings in bodies of water or down sewer drains. Clean dried sealer on tools using wire brushing, scraping and peeling.

INSTALLATION: Prior to use, user must read and follow Installation Instructions for ACTION PAVE® RT CLASSIC to verify product selection, pavement preparation procedures, mixing, application rates, usage precautions and safety procedures. General guidelines are as follows: Preparatory Work — The asphalt surface must be structurally sound, surface cured, and free from all loose or foreign matter prior to the application of ACTION PAVE® RT CLASSIC. ACTION PAVE® RT CLASSIC can be applied by spray, rubber-bladed squeegee, brush, or mechanical equipment specifically designed for this purpose. Due to the heavy bodied nature of the slurry-mixed ACTION PAVE® RT CLASSIC, application by means of specialized equipment is recommended. This equipment can be of two types, high volume positive displacement airless spray or mechanical squeegee. Both types must be capable of keeping material thoroughly mixed and homogenous throughout the application process. All equipment used must be capable of supplying a sufficient quantity of material for uniform application over the entire width of the application mechanism to provide a uniformly coated surface.

Curing Time

Cure time will vary according to temperature and humidity at the time of application. Insufficiently cured films wear prematurely. Lower temperatures, high humidity and lack of direct sunlight will prolong the cure time. Higher temperatures, lower humidity and direct sunlight accelerate the cure process. If a second coat is to be applied, allow the first coat to dry sufficiently to withstand light vehicular and pedestrian traffic without damaging or scuffing the coating. After the application of the last coat, allow the coating to cure at least 20-24 hours under good drying conditions prior to opening to traffic.

Special Instructions

ACTION PAVE® RT CLASSIC must be applied on structurally sound pavement surfaces. Apply only on unsealed asphalt or surfaces previously sealed with either Asphalt Emulsion or Refined Tar based Sealers. Do not apply over surfaces sealed with gilsonite and other solvent based sealers. New asphalt pavements must be allowed to cure at least 90 days in hot weather. Perform a water break free test to confirm that the surface oils have dissipated, by spreading water on the pavement. If the water does not bead, pavement is ready for sealcoating. Not recommended for steeply inclined surfaces, as they may become slippery when wet.

Cautions

KEEP FROM FREEZING / KEEP OUT OF REACH OF CHILDREN

Keep stored containers sealed tightly.

Contains refined coal tar. May cause skin irritation. Wear gloves and protective clothing. In case of contact, flush skin or eyes immediately with fresh water. If the product gets in the mouth or eyes see a physician immediately. Consult the Safety Data Sheet for details.

Packaging and Availability

55-gallon drums & 275-gallon plastic totes, and bulk sold by the gallon.

WARRANTY: ACTION PAVE® RT CLASSIC is warranted by the manufacturer to meet specification requirements at time of shipment. Techniques used for pavement preparation prior to sealer application are beyond manufacturer control as are use and application of sealer; therefore, the manufacturer shall not be responsible for improperly applied or misused sealer. Remedies against the manufacturer are limited to replacing nonconforming product or refund (full or partial) of purchase price. All claims for breach of this warranty must be made within three (3) months of delivery date. There shall be no other warranties expressed or implied. **For optimum performance, follow recommendations for sealer installation.**